

ClimaFoam® XPS Board

Thickness (mm)	Thermal conductivity (W/mK)	R-Value (m ² K/W)	Length (mm)	Width (mm)	Joint Type	Compressive strength (kPa)
ClimaFoam XPS Board - 1200mm wide						
30	0.027	1.1	2200	1200	Shiplap	300
40	0.027	1.5	2200	1200	Shiplap	300
50	0.027	1.8	2200	1200	Shiplap	300
75	0.027	2.8	2200	1200	Shiplap	300
100	0.027	3.7	2200	1200	Shiplap	300
30	0.027	1.1	2200	1200	T&G	300
40	0.027	1.5	2200	1200	T&G	300
50	0.027	1.8	2200	1200	T&G	300
75	0.027	2.8	2200	1200	T&G	300
100	0.027	3.7	2200	1200	T&G	300

Knauf Insulation Pty Ltd

Building 1, Unit 2, 15 Accent Drive
East Tamaki, Auckland, 2013

Customer Service (Sales)

Tel: 0800 562 834
Tel: +61 7 3393 7300
Fax: +61 7 3902 0613
Email: orders.nz@knaufinsulation.com

Technical Advisory Centre

Email: tech.nz@knaufinsulation.com

knaufinsulation.co.nz